

## **BOWSCAR LAZONBY**

Origin	Bowscar, Penrith
Density kg/m <sup>3</sup>	2367 kg/m <sup>3</sup>
Water Absorption %	2.2-2.7% wet
Compressive Strength	93-118 MPA
Porosity %	10.3-13.1%
Abrasion Resistance	18.4-19.6
Flexural Strength	3.6 MPA
Slip Resistance (wet)	76-80
Salt Crystallisation	0.23% mean wt loss
Saturated Coefficient	5.1 mean wt loss
Slip Resistance (dry)	Not Determined