

Doddington

Density kg/m³ – 2201 - 2135

Flexural Strength – 3.4 MPa

Water Absorption % – 4.3 - 5.2%

Slip Resistance (wet) – 78

Compressive Strength – 51.3 - 58.2 MPA

Salt Crystallisation – 90% Mean wt loss

Porosity % – 14.8%

Saturated Coefficient – 0.62 - 0.65

Abrasion Resistance – 23.2

Slip Resistance (dry) – Not Determined

Acid Immersion – Pass