

NORTHUMBERLAND BUFF

Density (kg/m ³)	2110
Compressive Strength (N/mm ³)	55.1
Absorbtion (%)	6.13
Saturation Coefficient	0.63
Porosity (%)	20.52
Acid Immersion	testpass
Salt Crystallisation (%)	-0.70
Flexural Strength (dry/perp)(N/mm ²)	3.1