

ORTON SCAR LIMESTONE

| | |
|--------------------------------------|------------------------|
| Slip Resistance | Not Determined |
| Abrasion Resistance | Not Determined |
| Strength under load | |
| 1) Compression | 95 MPa |
| 2) Bending | Not Determined |
| Porosity and Water Absorption | |
| 1) Porosity | 0.9 - 2.9% |
| 2) Saturation Coefficient | 0.69 - 0.80 |
| 3) Water Absorption | 0.35% (by wt) |
| 4) Bulk specific gravity | 2675 kg/m ³ |
| Resistance to Frost | |
| Freeze/Thaw Test | Not Determined |
| Resistance to Salt | |
| Sodium Sulphate Crystallisation Test | Mean: 0% |