

## **SALTERWATH LIMESTONE**

Origin	Orton, Cumbria
Density kg/m <sup>3</sup>	2.687 kg/m <sup>3</sup>
Water Absorption %	1.20%
Compressive Strength	102 mpa
Porosity %	0.4 - 4.7%
Abrasion Resistance	Not Determined
Flexural Strength	18.7 mpa
Slip Resistance (wet)	Not Determined
Salt Crystallisation	0.01% mean wt loss
Saturated Coefficient	0.92 mean wt loss
Acid Immersion	Durability Class A